



HANGZHOU SUNGLOW CHEMICAL CO., LTD.
6F, Block 4, Orient International Plaza, No.60 North Shixin Road, Xiaoshan,
Hangzhou 311215, China
Tel : +86 571 8273 7745 E-mail: sales@sunglowchem.com
Fax: +86 571 8273 7745 Web: www.sunglowchem.com

TECHNICAL DATA SHEET

Product Description:

	PIGMENT YELLOW 138 L
Product Name:	Pigment Yellow 138 L
Color Index:	Pigment Yellow 138
C.I.NO.:	56300
Chemical Nature:	Quinophthalone
CAS No.:	30125-47-4
Chemical Formulation:	C26H6Cl8N2O4
	Full Shade
	Reduced Shade

Physical Data:

Appearance	Yellow Powder
Density (g/cm3)	1.8
Moisture (%)	≤1.0
Water Soluble Matter (%)	≤1.0
Oil Absorption (g/100g)	30-40
Fineness (80mesh dry method) %	≤5.0
PH Value	6.0-7.0
Conductivity (us/cm)	≤500

Fastness Properties (5=excellent, 1=poor):

Bleeding Resistance	5
Migration Resistance	-
Light Fastness (8=excellent)	8
Heat Resistance °C	200
Acid Resistance	5
Alkali Resistance	5

Product Features:

Pigment Yellow 138 L is a green-shade yellow pigment with good light and weather fastness properties.

Recommended Application:

Coating and Paint.