



HANGZHOU SUNGLOW CHEMICAL CO., LTD.

6F, Block 4, Orient International Plaza, No.60 North Shixin Road, Xiaoshan, Hangzhou 311215, China

Tel : +86 571 8273 7745

E-mail: sales@sunglowchem.com

Fax: +86 571 8273 7745

Web: www.sunglowchem.com

TECHNICAL DATA SHEET

Product Description:

Product Name:	Pigment Yellow 62
Color Index:	Pigment Yellow 62
C.I.NO.:	13940
Chemical Nature:	Monoazo Lake
CAS No.:	12286-66-7
Chemical Formulation:	C17H15N4O7S1/2Ca

PIGMENT YELLOW 62



Full Shade



Reduced Shade

Physical Data:

Appearance	Yellow Powder
Density (g/cm ³)	1.4
Moisture (%)	≤2.0
Water Soluble Matter (%)	≤1.5
Oil Absorption (g/100g)	35-45
Fineness (80mesh dry method) %	≤5.0
PH Value	6.0-8.0
Conductivity (us/cm)	≤500

Fastness Properties (5=excellent, 1=poor):

Bleeding Resistance	-
Migration Resistance	4
Light Fastness (8=excellent)	7
Heat Resistance °C	260
Acid Resistance	5
Alkali Resistance	5

Product Features:

Pigment Yellow 62 is a strong yellow pigment with good light fastness and heat resistance.

Recommended Application:

Plastic.